

# TECHNICAL DATA SHEET WOOD FIBER SHEATHINGS

## 7/16" REGULAR SHEATHING

### **DESCRIPTION:**

The **Sheathing 7/16"** is a rigid panel produced from non-toxic organic materials and natural wood fibres. All panels are asphalt coated on both sides for greater weather resistance. **Sheathing 7/16"** panel has excellent water vapour permeance which allows interior water vapour to escape to the exterior and not be trapped within the wall cavity where it could cause damage.

### USES:

Sheathing 7/16" panel is an excellent base for use on the exterior of frame construction due to its excellent permeance and weather resistance.

### STORAGE:

Wood fibre panels must be stored 100 mm (4") above ground level and adequately protected from the elements with tarpaulins.

Sizes and Packaging									
SKU	Dimensions Panels/Bundle		Coverage/bundle						
BSSHT75 []	1219 mm x 2286 mm 48" x 90"	110	306.6 m <sup>2</sup> (3300 ft <sup>2</sup> )						
BSSHT8 []	1219 mm x 2438 mm 48" x 96"	110	327.2 m <sup>2</sup> (3520 ft <sup>2</sup> )						
BSSHT9 []	1219 mm x 2743 mm 48" x 108"	110	368 m <sup>2</sup> (3960 ft <sup>2</sup> )						

CHARACTERISTICS	Units		RESULTS BP		REQUIREMENTS		Test Method
	METRIC	IMPERIAL	METRIC	IMPERIAL	METRIC	IMPERIAL	
Nominal Thickness	mm	in	11.10	0.437	11.1	0.4375	ASTM C209
Thermal Resistance min., 25.4 mm (1")	RSI	R	0.53	3.00	≥0.410	≥2.33	ASTM C518
Water Vapour Permeance min.	ng/(Pa• s•m²)	perms	2109	37.70	287	4.99	ASTM E96
Transverse Load at Rupture, min avg	N	lbf	48	10.8	48	10.8	ASTM C209
Tensile Parallel to Surface	kPa	lb/in²	2030.0	294.4	1000	145	ASTM C209
Linear Moisture Expansion max.	%	%	0.2	0.2	0.5	0.5	ASTM D1037
Water Absorption max. 2 hours	%	%	3	3	7	7	ASTM C209

### **APPLICABLE STANDARDS**

CAN/ULC S706-09, Type II, Class 3, Grade 1 CCMC-12044-L